

Technical information sheet

Glass fiber reinforcing tape



Product Name

Speedline Glass fiber reinforcing tape

Product Description

This high-quality product is composed of glass fibers with a carefully defined diameter and length. Thanks to its unique structure, where the fibers are randomly laid lengthwise and reinforced with a binder, a fleece is created that is exceptionally dimensionally stable and offers high wet strength. Ideal for reinforcing joint fillers in plasterboard – for a durable, crack-free, and smooth finish.

Standard Size

Roll Width: 50 mm (± 2 mm)

Roll Length: 25 m ($\pm 1\%$)

Packaging

In white cardboard.

Packaging Unit

40 rolls per box, 60 boxes per pallet.

Weight per Packaging Unit

Approx. 2.2 kg per box, approx. 150 kg per pallet.

Technical Data

Tested Property	Nom. Value	Tolerance	Test Standard
Surface weight	33 g/m ²	± 3	DIN EN 29073-1
Fibers	13 μ m, 12 mm	-	-
Loss on ignition	18%	± 3	DIN EN 13820
Thickness	0.37 mm	± 0.03	DIN EN ISO 9073-2
Tensile strength MD	105 N/5 cm	-30	DIN EN 29073-3
Tensile strength CMD	80 N/5 cm	-25	DIN EN 29073-3
Air permeability	4.700 l/m ² /s	-	DIN EN ISO 9237
@ 100 PA	4,700 l/m ² /s	-	DIN EN ISO 9237
Fire behaviour	E	-	DIN EN 13501-1



Recommended storage

Keep dry during storage and transport.

Details

This product is an article according to Regulation (EC) No. 1907/2006 (REACH) and is not classified as hazardous, nor does it require labeling according to CLP Regulation 1272/2008 on the classification, labeling, and packaging of substances and mixtures.

The data are empirical values based on the current production status and are subject to normal tolerances. They do not represent guaranteed properties.

We reserve the right to make technical changes.

Disclaimer

The information in this document is intended to inform our customers. It is intended as a guide only and should not be considered a guarantee or quality specification. We are not liable for any (direct or indirect) damage resulting from the use of the product shown in this document. The user is responsible for performing all necessary tests to ensure that the product is suitable for the intended application. We have no influence on the application method of the product or the conditions during storage and transport. We accept no liability for any (typesetting) errors or omissions. This document replaces previous versions.

Scan for product page



info@speedline.nl
www.speedline.nl/en-gb